



Duraflex DF Series

Duraflex DF is a UV curable ink system specifically formulated for flat, pressure sensitive decal applications requiring exterior exposure for five years. Extensive weathering tests have proven Duraflex yields resilient decals, which will not edge curl due to ink/vinyl shrinkage or diminish in color intensity. Duraflex has been formulated with lead free, automotive grade pigments producing an extremely opaque, remarkably high gloss, lightfast ink film with minimal chalking characteristics.

Version 1.04.20.2005

Performance Properties

- Suitable for five (5) year exterior exposure
- Exceptional opacity and high gloss
- Extremely flexible for multi-layer applications and die-cutting
- Low shrinkage, which diminishes edge curl
- Suitable with pre-mask films for easy application
- Non-blocking, low tack finish for easy handling
- Solvent and abrasion resistant

Printing

Mix well prior to use. While supplied in press ready condition, DF may be reduced up to 10% with DF Thinner for special viscosity adjustments. Care should be taken to print the ink at optimal temperature 70 - 90°F (21 - 27°C). Cool ink will have heavier viscosity and will not flow properly, whereas hot ink will be lower in viscosity, resulting in poor definition and decreased opacity.

Coverage

3,200 to 3,600 square feet per gallon based on ink deposit of .40 – .60 mil, dependant on color and printing conditions.

Curing

Ink will cure well when printed through 355 (140cm) plain weave polyester mesh or finer. DF's optimal cure window of 175 - 200 mJ / 550 - 650 mW is generally achieved with one 200 watt per inch mercury vapor lamp at belt speeds between 50 - 60 feet per minute (20 - 30 m/min). This should provide thorough cure of the product. Cure speeds may vary as thicker material and dark surface colors require more energy. Adhesion should be a minimum of 95% from curing unit with final adhesion developing within four hours of initial polymerization. Coarser fabrics can be utilized, however, cure parameters may need to be adjusted for increased ink film. If a loss of gloss or adhesion due to insufficient cure is noticed, the use of 5 - 10% DF Mixing Clear will increase light penetration and improve cure.

Recommended Substrates

- Pressure Sensitive Vinyl
- Print Treated Polyester
- Electrostatic vinyl
- Polycarbonate (adhesive not recommended)
- PVC
- Vinyl coated magnets
- Polystyrene
- Coated paper
- Many coated metals

Lightfastness

DF is lightfast up to five (5) years with a 355/inch or coarser mesh. Weathering tests have been completed on 4-mil vinyl, printed with DF Series. The ink withstood 2,500 hours of exposure with 4-hour cycle times of light and condensation at elevated temperatures with minimal color change and no shrinkage. To maintain a high gloss finish use DF Overprint Clear.

Accelerated machine weathering's are reference standards and can not precisely reproduce actual outdoor performance. Based on prior correlation of accelerated testing vs. real time exposure, 500 hours is equated to approximately one year, 45° south Florida.

The use of premium grade, long-term vinyl films are recommended for applications intended to weather three (3) years or longer. Solar Shield Clear UV absorbers have been incorporated into the DF Solar Shield Overprint clear, which lengthen the graphics life by acting as a sunscreen. This clear requires more energy to cure than the normal Duraflex color range. A minimum of 225 - 250 mJ is needed.

Pre-Mask

A medium to high tack adhesive is recommended for good adhesion.

Storage

Care should be taken to store ink in tightly closed containers located in a cool (60 - 80°F / 15 - 27°C) dark place. After long production runs excess ink from the screen should be properly disposed. With suitable conditions, unopened ink is expected to have a shelf life of approximately twelve (12) months from date of manufacture.

Metallic's

Use the Metallic Mixing Clear to prepare metallic ink as it's increased viscosity helps insure a good particle suspension and extended shelf life. Recommended mixing ratios, by weight are:

- 28% gold paste
- 12% silver paste

For optimum coverage and opacity, 280 - 305 (110 - 120cm) plain weave mesh is recommended. Use DF Overprint Clear for extended weatherability and improved non-tarnishing properties of the product.

Additives

- 1004 Thinner up to 10% as needed
- 1534 Adhesion Promoter, 3-5% as needed

Precautions

Read the material safety data sheet prior to processing. It contains instructions for precautions to be taken when handling inks. If ink comes in contact with skin, wipe ink off with a clean, dry cloth (do not use solvent). Wash and rinse the affected area with soap and water.

Process Printing

For superior halftone reproduction, Duraflex halftones are available in a range of density levels. Additional control of density may be achieved with use of DF HT Base. For best results, 380 (150 cm) or finer and a smooth, thin stencil coating should be utilized with process printing.

	Press Ready	High Density	Backlit Density
DF Halftone Yellow	0.90	1.10	1.35
DF Halftone Magenta	1.40	1.75	2.05
DF Halftone Cyan	1.40	1.80	2.20
DF Halftone Black	1.60	2.00	2.25

We strongly recommend a preliminary test of printing and curing on the supports intended to use, in order to ascertain exactly the procedure, the working times and the obtained effect. MIX WELL BEFORE USE. Follow the directions on the package, ask for the safety data sheets and always follow the directions contained therein.

IMPORTANT— Only the correct use of the product will allow satisfactory results. For this reason, closely related to the product supplied, Polymeric must decline all direct and indirect responsibility for the proper or improper use of the product. Make certain that product is right for the desired use, work according to the instructions given in our technical data sheets. Before use contact Technical Service in case of doubt.

POLYMERIC IMAGING, INC.—117 East 14th Avenue, North Kansas City, Missouri 64116 USA Tel: 816-221-5567 / 800-746-5567 sales@polymericimaging.com www.polymericimaging.com

Color Availability

Duraflex DF is available in twenty opaque standard colors. Custom matches, metallic, fluorescent and transparent colors are obtainable upon request.

DF-101 Primrose Yellow	DF-210 Ultra Blue
DF-111 Lemon Yellow	DF-220 Emerald Green
DF-123 Medium Yellow	DF-225 Forest Green
DF-131 Brilliant Orange	DF-226 Lime Green
DF-135 Vivid Orange	DF-235 Teal
DF-141 Fire Red	DF-240 Purple
DF-151 Scarlet Red	DF-260 Brown
DF-155 Rubine Red	DF-301 Opaque Black
DF-160 Rhodamine Red	DF-311 Opaque White
DF-180 Warm Red	DF-312 Dense Black
DF-190 Process Blue	DF-026 Brilliant White
DF-200 Peacock Blue	DF Overprint Clear
DF-205 Reflex Blue	DF Metallic Mixing Clear

Pantone Matching System® Colors

The nine PANTONE® approved Color Matching System (CMS) shades are used to simulate the PANTONE Color Specified colors. Formulas were designed for maximum opacity and are available in book or Imaging Color Source Software formats.

DF-064 CMS GS Yellow	DF-066 CMS RS Yellow
DF-114 CMS Orange	DF-121 CMS YS Red
DF-164 CMS BS Red	DF-165 CMS Magenta
DF-127 CMS Violet	DF-230 CMS Blue
DF-325 CMS Green	DF Tinting White
DF Shading Black	DF Mixing Clear

PANTONE® is a trademark of Pantone, Inc. Portions © Pantone, Inc., 1963, 1991.